



# APTIV™ FILMS 1300

## General Information

### Product Description

APTIV 1300 film is the black version of unfilled semi-crystalline films made from VICTREX™ PEEK polymer. The film provides a material solution for engineers in ultra-high performance applications offering an alternative option to the APTIV 1000 natural product.

APTIV 1300 film has a unique combination of properties providing high temperature performance, light weight, mechanical strength, durability, excellent radiation, hydrolysis and chemical resistance, electrical insulation, wear and abrasion resistance, excellent barrier properties with high purity, good flammability without the use of flame retardants, low toxicity of combustion products and low moisture absorption in a film format. Inherently halogen free and providing ease of processing makes APTIV films a technology enabler for OEMs, our customers and end users.

## Material Properties

Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.30	g/cm <sup>3</sup>	ISO 1183
ShrinkageMD <sup>1</sup> (200°C, 50.0 µm)	< 2.0	%	
ShrinkageTD <sup>1</sup> (200°C, 50.0 µm)	< 2.0	%	
Films	Nominal Value	Unit	Test Method
Film Thickness - Recommended / Available	50 to 100	µm	
Tensile Modulus			ISO 527-3
MD : 23°C, 50 µm	2500	MPa	
TD : 23°C, 50 µm	2500	MPa	
MD : 23°C, 100 µm	2400	MPa	
TD : 23°C, 100 µm	2300	MPa	
Tensile Stress			ISO 527-3
MD : Break, 23°C, 50 µm	120	MPa	
TD : Break, 23°C, 50 µm	110	MPa	
MD : Break, 23°C, 100 µm	120	MPa	
TD : Break, 23°C, 100 µm	110	MPa	
Tensile Elongation			ISO 527-3
MD : Break, 23°C, 50 µm	> 150	%	
TD : Break, 23°C, 50 µm	> 150	%	
MD : Break, 23°C, 100 µm	> 150	%	
TD : Break, 23°C, 100 µm	> 150	%	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity <sup>2</sup> (23°C, 50 µm)	4.0E+16	ohms·cm	ASTM D257
Dielectric Strength <sup>3</sup> (23°C, 50 µm)	190	kV/mm	ASTM D149

## Notes

<sup>1</sup> TM-VX-84

<sup>2</sup> 100 V

<sup>3</sup> 0.25 inch electrode

Revision Date: November 2023

This information is provided "as is". It is not intended to amount to advice. Use of the product is at the customer's/user's risk. It is the customer's/user's responsibility to thoroughly test the product in each specific application to determine its performance, efficacy and safety for each end-use product, device or other application and compliance with applicable laws, regulations and standards. Mention of a product is no guarantee of availability. Victrex reserves the right to modify products, data sheets, specifications and packaging. **Victrex makes no warranties, express or implied (including, without limitation, any warranty of fitness for a particular purpose or of intellectual property non-infringement) and will not be liable for any loss or damage of any nature (however arising) in connection with customer's/user's use or reliance on this information, except for any liability which cannot be excluded or limited by law.** This document may be modified or retracted at any time without notice to the customer/user.

Victrex Manufacturing Limited (or another member of the Victrex group) is the owner or the licensee of all intellectual property rights in and to this document including the following trademarks, VICTREX, 450G, VICTREX AM, VICTREX CT, VICTREX FG, VICTREX HPG, VICTREX HT, VICTREX ST, VICTREX WG, APTIV, LMPAEEK, VICOTE, TRIANGLE (Device). All rights are protected by intellectual property rights including copyright under relevant national and international intellectual property laws and treaties. All rights reserved. Copyright © Victrex Manufacturing Limited 2025.