

Production

CERAMILL PEEK by JUVORA™ blanks can only be processed on suitable milling machines with appropriate milling programs. The milling head must be suitable for machining PEEK polymer. Juvora Ltd recommends suitable adaptation of the CAM software by the software manufacturer to allow milling of the CERAMILL PEEK by JUVORA™. For an exact fit, a 5-axis milling machine is recommended. Juvora Ltd also recommends cooling the milling head for more accurate milling and to prolong its useful life.*See footnote.

Prosthesis removal from the JUVORA™ dental disc

Remove the prosthesis carefully from the blank using a hard metal cutter, and pay particular attention to the edges of the prosthesis.

Safety Information

While machining CERAMILL PEEK by JUVORA™, the following safety precautions are recommended:

- Dust mask or dust extraction
- Personal protective equipment (eye protection, gloves)

The EUH210 and EUH212 warning statements present on label relate to EU Regulation (EC) No 1272/2008 only.

Storage Information

CERAMILL PEEK by JUVORA™ should be stored in dry storage and avoid exposure to direct sunlight. The PEEK polymer from which CERAMILL PEEK by JUVORA™ is made is stable and can be stored for an extended period of time (10 year shelf life). It has a working temperature range from cryogenic up to 250°C and hence the storage temperature range for CERAMILL PEEK by JUVORA™ is any ambient temperature and humidity.

Additional Information

For additional information contact info@invibio.com
Juvora Ltd: Technology Centre, Hillhouse International, Thornton Cleveleys, Lancashire, FY5 4QD, UK
Tel: +44 (0)1253 898000 · www.invibio.com

*Note: Follow the instructions of your machine manufacturer regarding the processing of CERAMILL PEEK by JUVORA™.
Download processing instructions @
www.amanngirrbach.com/instruction-manuals.

Juvora

CERTIFIED
DISTRIBUTOR



AMANNGIRRBACH

INSTRUCTIONS FOR USE

CERAMILL PEEK by JUVORA™

Caution: US Federal Law restricts this device to sale by or on the order of a dentist

Indications

- For the manufacture of:
 - i) full and partial removable dentures and implant overdentures.
 - ii) copings, substructures (cemented or uncemented), frameworks for permanent and transitional anterior or posterior crowns and bridgework.

Contraindications

Not to be used in bridges with 2 or more pontics.

Precautions

To be manufactured with material thickness/size in accordance with the following:

- The minimum thickness of secondary crowns and matrix housings should not be less than 0.7 mm
- The minimum thickness for “conventional” retention grids should not be less than 2 mm.
- Minimum size of horizontal retainer in lower jaw 2 mm x 8 mm
- Minimum size of horizontal band in upper jaw 2 mm x 8 mm

Warning:

- Do not mill the frameworks too thin. Follow the milling parameter guidance provided in the Juvora Processing Guide
- Do not repair or extend frameworks after milling or initial implantation

Material Information

CERAMILL PEEK by JUVORA™ are manufactured from Invibio PEEK polymer, a Type 3 thermoplastic according to ISO 20795 – Denture Base Polymer.

Form:	Solid
Odour:	Odourless
pH (Value):	Not known
Boiling Point (°C):	Not known
Melting Point (°C):	343
Flash Point (°C):	Not known
Auto Ignition Temperature (°C):	595
Oxidising Properties:	Not applicable
Vapour Pressure (Pascal):	Not known
Solubility (Water):	Insoluble

Processing Instructions

Detailed processing instructions are provided and must be observed by the end users (dental labs and technicians) when milling frameworks from the CERAMILL PEEK by JUVORA™. Dental labs that are supplied with the disc will be certified through Juvora Ltd, a process that involves assessment of their capability to follow the processing guidance to manufacture high quality frameworks and finished dentures where applicable using their existing equipment. This assessment will be completed by Juvora Ltd or Amann Girrbach or a certified milling centre of Juvora Ltd or Amann Girrbach. Find more information about the processing of PEEK @ www.juvoradental.com/academy